

STEK

Technical Data Sheet

Product Name	DYNOred.				
Application	Paint Protection Film				
Thickness	215±10µm				
Properties	Properties	Unit	Value	Test Method	
	Thickness	µm	215±10	Thickness gauge	
	Coating layer crack	MD	mm	40	ASTM D 412
		TD	mm	42	
	Self-healing	sec	under 30	Room Temp.	
	Adhesion (30 min)	gf/25mm	> 1500	ASTM D3330	
	Adhesion (24 hours)	gf/25mm	> 2400		
Product Structure					
Characteristic	<ul style="list-style-type: none"> - Super Hydrophobic with Instant Self-healing at once - No water stain or easy to remove it by general car wash - Extrem high gloss without yellowing - Anti-Contamination - Impact resistance 				